

1. Report No. MR 2004-03	2. Report Date November 25, 2008	3. Contract No. N/A	4. Project No. AC-NH-2-281(025)049
5. Title and Subtitle Evaluation of Rumble Stripes		6. Report Type Click on link to open report Work Plan <input type="checkbox"/> Construction <input type="checkbox"/> Evaluation <input type="checkbox"/> <u>Final</u> <input checked="" type="checkbox"/>	7. Project No. 8. Project No. 9. Project No. 10. Project No.
11. Author(s)/Principle Investigator(s) Steven Henrichs, Matthew Luger		12. Performing Organization Name and Address 13. Sponsoring Agency Name and Address North Dakota DOT Materials and Research Division 300 Airport Road Bismarck ND 58504-6005	
12. Performing Organization Name and Address NDDOT M+R <input checked="" type="checkbox"/> North Dakota DOT NDDOT OTHER* <input type="checkbox"/> Materials and Research Division NDSU <input type="checkbox"/> 300 Airport Road UND <input type="checkbox"/> Bismarck ND 58504-6005 UGPTI <input type="checkbox"/> OTHER* <input type="checkbox"/> *see supplementary notes		13. Sponsoring Agency Name and Address North Dakota DOT Materials and Research Division 300 Airport Road Bismarck ND 58504-6005	
14. Supplementary Notes			
15. Abstract <u>Purpose and Need</u> Water on the surface of pavement markings typically reduces the marking's retroreflectivity and may cause pavement markings to become nearly invisible during wet conditions at night. Water on the surface of pavement markings reflects light away from its source and doesn't allow the beads in the pavement marking to reflect light back towards its source. This condition is referred to as "wet-night" and the retroreflectivity during this condition is referred to as "wet-night retroreflectivity". To improve a marking's wet-night retroreflectivity, some states have experimented with placing markings on rumble strips. This may improve wet-night retroreflectivity by providing a slanted surface that quickly drains water off the surface of the marking. The placement of pavement markings on rumble strips has been referred to as "rumble stripes". <u>Objective</u> The objective is to determine if placing pavement markings on rumble strips will improve the marking's wet-night retroreflectivity. <u>Scope</u> To test the effectiveness of rumble stripes, the NDDOT has constructed a test section as part of project AC-NH-2-281(025)049. This project was a rehabilitation of a two-lane US Highway that serves as an interregional corridor across North Dakota. The rehabilitation consisted of a new asphalt surface constructed on a blended base. The entire project had rumble strips ground into both shoulders. A three mile test section was selected by the Valley City District. The test section was constructed using a modified location of the rumble strips on both shoulders. The edge lines were placed on the rumble strips. <u>Summary</u> The position of the markings on the rumble strip doesn't appear to greatly affect the day-time appearance of the marking. The application of marking paint on incompletely cured fog seal material may have caused adhesion and durability problems. Materials and Research personnel have observed that rumble stripes appear to have better visibility than the usual edge marking in both wet and dry conditions. Comments collected from Jamestown Section personnel support Materials and Research observations. Wet-night retroreflectivity readings were mostly inconclusive in showing improvement in retroreflectivity. Further research is needed to make definite statements based on retroreflective data. It is recommended to further evaluate rumble stripes by placing markings within the rumble strips of an existing roadway. This could be used to do a side-by-side comparison of rumble stripes with the usual edge markings and to evaluate if this configuration may be used on existing roadways. Chip seal projects are a good opportunity to install the replacement edge line striping in a rumble strip, thereby creating a rumble stripe.			
16. Key Words Pavement Marking on Rumble Strip Rumble Stripe	17. Distribution Statement No restrictions. This document is available to the public from: North Dakota Department of Transportation Materials and Research Division: 300 Airport Road Bismarck ND 58504-6005 Office: (701) 328-6900 Fax: (701) 328-0310		18. No. of Pages 16 19. File type/Size PDF/0.4 MB